

Pro Gold Lite

| Property | Test Method | English | Metric |
|--|-------------|---------------|-----------------------|
| Color | Observed | Black | Black |
| Line Spacing | Observed | 12 in | 12 in |
| Polymer | Observed | Polypropylene | Polypropylene |
| Construction | Observed | Woven | Woven |
| Typical Weight | ASTM D-3776 | 2.7 oz/sy | 70 GSM |
| Grab Tensile (MD) | ASTM D-4632 | 100 lbs | 45 KG |
| Grab Tensile (CD) | ASTM D-4632 | 100 lbs | 45 KG |
| Trapezoid Tear | ASTM D-4533 | 50 x 50 lbs | 23 x 23 KG |
| Puncture | ASTM D-4833 | 50 lbs | 23 KG |
| Water Permeability | ASTM D-4491 | 2.1 gpm/sf | NA LPM/M ² |
| Ultraviolet Exposure (% Strength Retained) | ASTM D-4355 | >70% % | >70% % |

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.